

Physical properties		Standard
Density	97.8% - 7.8g/cm ³	ASTM B311
Mechanical properties		
Tensile Strength, Ultimate	594 Mpa	ASTM E8 / E8M
Tensile Strength, Yield	265 Mpa	ASTM E8 / E8M
Modulus of Elasticity	175 Gpa	ASTM E8 / E8M
Elongation at break	45.6%	ASTM E8 / E8M
Hardness HRB	86	ASTM E18 - 20
Shrinkage per dimension	15.5%	
Thermal properties		
Coefficient of Thermal Expansion		
	14.6 25°C	ASTM E831-19
	17.0 100°C	ASTM E831-20
	18.1 300°C	ASTM E831-21
	19.8 500°C	ASTM E831-22
Others		
Carbon residuals	< 0.03%	
Storage conditions	15-35 ° C , 50% relative humidity, non-condensing	
Suitable protection	Wear suitable protective clothing, gloves and eye/face protection	
Risk phrases	H20/H22: Harmful if inhaled or swallowed H37/37/38: Irritating to eyes, respiratory system and skin	
First aid	Skin contact: rinse with large amounts of water and soap Refer for medical attention as necessary Do not use solvents or thinners	
Ingestion inhalation	DO NOT induce vomiting. Get medical attention immediately	
Shelf life	1 year	

All data provided herein is for information purposes only, is provided on an "as is" basis, without warranty of any kind, express or implied, and should not be relied upon or considered specific advice to any customer project. Any product and materials information provided herein is subject to terms and conditions as may be agreed upon by XJet in writing. All measurements, to the extent detailed, are based on internal testing made on lab specimens by XJet or on its behalf, and the actual performance or results of any product may vary. XJet reserves the right to change the terms and conditions under which its products are offered at any time.

